



TEST REPORT

Report No. : WTF22F10216847C

Applicant : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan,
Kowloon, Hong Kong

Manufacturer : 111919

Sample Name : RPET picnic blanket with PEVA backing

Sample Model : MO6891

Test Requested : 1) Determination of Lead content in the submitted sample in accordance with REACH regulation Annex XVII Entries 63 (EC) No. 1907/2006 and the amendment No. 836/2012 and (EU) 2015/628
2) Determination of Cadmium content in the submitted sample in accordance with REACH regulation Annex XVII Entries 23 (EC) No. 1907/2006 and the amendment No. 552/2009, No. 494/2011, No. 835/2012 and (EU) 2016/217
3) Determination of specified Phthalates content according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 & No. 2018/2005
4) Determine the specified AZO Colorants contents in the submitted sample in according to the Entries 43 in Annex XVII of the REACH Regulation (EC) No.1907/2006 and the Amendment Regulation (EC) No.552/ 2009 & No.126/ 2013 (previously restricted under Directive 2002/61/EC).
5) As requested by the applicant, to test Colour Fastness to Rubbing in the submitted sample.

Test Conclusion : Refer to next page (s)

Date of Receipt sample : 2022-10-31

Testing period : 2022-10-31 to 2022-11-04

Date of Issue : 2022-11-07

Test Result : Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City,
Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of
Waltek Testing Group (Foshan) Co., Ltd.

Swing Liang

Swing.Liang
Waltek Testing Group (Foshan) Co., Ltd.
<http://www.waltek.com.cn>



Report No.: WTF22F10216847C

Sample photo:



1



2



3





Report No.: WTF22F10216847C

Test Results:

1) Lead (Pb)

Test Method: With reference to IEC 62321-5:2013, the analysis was performed by ICP-OES.

Test Item	LOQ (mg/kg)	Results (mg/kg)		Limit (mg/kg)
		No.1+No.2+No.3	No.4+No.7	
Lead(Pb)	2	ND*	ND*	500
Conclusion	--	Pass	Pass	--

Test Item	LOQ (mg/kg)	Results (mg/kg)		Limit (mg/kg)
		No.5+No.6	No.8	
Lead(Pb)	2	58*	ND	500
Conclusion	--	Pass	Pass	--

Test Item	LOQ (mg/kg)	Results (mg/kg)			Limit (mg/kg)
		No.9	No.10+No.11	No.12	
Lead(Pb)	2	39	ND*	ND	500
Conclusion	--	Pass	Pass	Pass	--

Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than LOQ)
- (3) LOQ = Limit of quantitation
- (4) Limit of Lead was quoted from REACH regulation Annex XVII Item 63 (EC) No. 1907/2006 and the amendment No. 836/2012 and (EU) 2015/628.
- (5) "*" = Results are calculated by the minimum weight of mixed components.



Report No.: WTF22F10216847C

2) Cadmium (Cd)

Test Method: With reference to IEC 62321-5:2013, the analysis was performed by ICP-OES.

Test Item	LOQ (mg/kg)	Results (mg/kg)	
		No.1+No.2+No.3	No.4+No.7
Cadmium(Cd)	2	ND*	ND*
Conclusion	--	Pass	Pass

Test Item	LOQ (mg/kg)	Results (mg/kg)	
		No.5+No.6	No.8
Cadmium(Cd)	2	15*	ND
Conclusion	--	Pass	Pass

Test Item	LOQ (mg/kg)	Results (mg/kg)		
		No.9	No.10+No.11	No.12
Cadmium(Cd)	2	ND	ND*	ND
Conclusion	--	Pass	Pass	Pass

Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than LOQ)
- (3) LOQ = Limit of quantitation
- (4) Limit of Cadmium according to REACH regulation Annex XVII Item 23 (EC) No. 1907/2006 and the amendment No. 552/2009, No. 494/2011 and No. 835/2012 and (EU) 2016/217.

Category	Limit (mg/kg)
Wet paint	100
Surface coating	1000
Plastic	100
Metal parts of jewellery and hair accessories	100

- (5) "*" = Results are calculated by the minimum weight of mixed components.



Report No.: WTF22F10216847C

3) Phthalates

Test Method: With reference to EN14372:2004, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Test Items	LOQ (%)	Results (%)	Limit (%)
		No.12	
Benzyl butyl phthalate (BBP)	0.005	ND	sum of four phthalates < 0.1
Di (2-ethyl hexyl)- phthalate (DEHP)	0.005	0.008	
Dibutyl phthalate (DBP)	0.005	ND	
Diisobutyl phthalate (DIBP)	0.005	ND	
Diisodecyl phthalate (DIDP)	0.01	ND	sum of three phthalates < 0.1
Diisononyl phthalate (DINP)	0.01	ND	
Di-n-octyl phthalate (DNOP)	0.005	ND	
Conclusion	--	Pass	--

Note:

DBP= Dibutyl phthalate

BBP= Benzyl butyl phthalate

DEHP= Bis-(2-ethylhexyl)- phthalate

DINP= Di-isononyl phthalate

DNOP= Di-n-octyl phthalate

DIDP= Di-isodecyl phthalate

DIBP= Diisobutyl phthalate

(1) % = percentage by weight

(2) ND = Not Detected or lower than limit of quantitation

(3) LOQ = Limit of quantitation

(4) "<" = less than

(5) The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) No.

1907/2006 & Amendment No. 552/2009 & No. 2018/2005 (formerly known as Directive 2005/84/EC) for phthalate content in toys and child care articles.



Report No.: WTF22F10216847C

4) AZO

Test Method: With reference to BS EN ISO 14362-1: 2017 and BS EN ISO 14362-3: 2017, analysis was performed by Gas Chromatographic Mass Spectrometry (GC-MS)

No.	Amines Substances	CAS No.	Limit (mg/kg)	Result (mg/kg)
				No.1+No.2+No.3
1	4-Aminobiphenyl	92-67-1	30	ND*
2	Benzidine	92-87-5	30	ND*
3	4-chloro-o-Toluidine	95-69-2	30	ND*
4	2-Naphthylamine	91-59-8	30	ND*
5	o-Aminoazotoluene	97-56-3	30	ND*
6	2-Amino-4-nitrotoluene	99-55-8	30	ND*
7	p-Chloroaniline	106-47-8	30	ND*
8	2,4-diaminoanisol	615-05-4	30	ND*
9	4,4'-Diaminodiphenylmethane	101-77-9	30	ND*
10	3,3'-Dichlorobenzidine	91-94-1	30	ND*
11	3,3'-Dimethoxybenzidine	119-90-4	30	ND*
12	3,3'-Dimethylbenzidine	119-93-7	30	ND*
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	30	ND*
14	p-cresinin	120-71-8	30	ND*
15	4,4'-Methylen-bis-(2-chloroaniline)	101-14-4	30	ND*
16	4,4'-Oxydianiline	101-80-4	30	ND*
17	4,4'-Thiodianiline	139-65-1	30	ND*
18	o-Toluidine	95-53-4	30	ND*
19	2,4-Toluylendiamine	95-80-7	30	ND*
20	2,4,5 – Trimethylaniline	137-17-7	30	ND*
21	o-anisidine	90-04-0	30	ND*
22	4-aminoazobenzene	60-09-3	30	ND*
23	2,4-Xylidin	95-68-1	30	ND*
24	2,6-Xylidin	87-62-7	30	ND*
Conclusion		--	--	Pass



Report No.: WTF22F10216847C

No.	Amines Substances	CAS No.	Limit (mg/kg)	Result (mg/kg)	
				No.5+No.6	No.12
1	4-Aminobiphenyl	92-67-1	30	ND*	ND
2	Benzidine	92-87-5	30	ND*	ND
3	4-chloro-o-Toluidine	95-69-2	30	ND*	ND
4	2-Naphthylamine	91-59-8	30	ND*	ND
5	o-Aminoazotoluene	97-56-3	30	ND*	ND
6	2-Amino-4-nitrotoluene	99-55-8	30	ND*	ND
7	p-Chloroaniline	106-47-8	30	ND*	ND
8	2,4-diaminoanisol	615-05-4	30	ND*	ND
9	4,4'-Diaminodiphenylmethane	101-77-9	30	ND*	ND
10	3,3'-Dichlorobenzidine	91-94-1	30	ND*	ND
11	3,3'-Dimethoxybenzidine	119-90-4	30	ND*	ND
12	3,3'-Dimethylbenzidine	119-93-7	30	ND*	ND
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	30	ND*	ND
14	p-cresinin	120-71-8	30	ND*	ND
15	4,4'-Methylen-bis-(2-chloroaniline)	101-14-4	30	ND*	ND
16	4,4'-Oxydianiline	101-80-4	30	ND*	ND
17	4,4'-Thiodianiline	139-65-1	30	ND*	ND
18	o-Toluidine	95-53-4	30	ND*	ND
19	2,4-Toluyldiamine	95-80-7	30	ND*	ND
20	2,4,5 – Trimethylaniline	137-17-7	30	ND*	ND
21	o-anisidine	90-04-0	30	ND*	ND
22	4-aminoazobenzene	60-09-3	30	ND*	ND
23	2,4-Xylidin	95-68-1	30	ND*	ND
24	2,6-Xylidin	87-62-7	30	ND*	ND
Conclusion		--	--	Pass	Pass

Note:

- ND = Not Detected or lower than limit of quantitation
- mg/kg=Milligram per kilogram
- Limit of quantitation (mg/kg): Each 5mg/kg
- The CAS-numbers 97-56-3 and 99-55-8 are further reduced to CAS-numbers 95-53-4 and 95-80-7.
- AZO colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline and 1,4-phenylenediamine. The presence of these colorants cannot be reliably ascertained without additional information, e.g. the chemical structure of the colorant used.
- The CAS-numbers 95-68-1 and 87-62-7 are not proscribed under REACH Regulation (EC) No 1907/2006
- “*” = Results are calculated by the minimum weight of mixed components.



Report No.: WTF22F10216847C

5) Colour Fastness to Rubbing

Colour Fastness to Rubbing					
(ISO 105-X12: 2016; Size of rubbing finger: 16mm diameter.)					
		No.1	No.2	No.3	Client's Limit
Length	Dry staining	4-5	4-5	4-5	2-3
	Wet staining	4-5	4-5	4-5	2-3
Width	Dry staining	4-5	4-5	4-5	2-3
	Wet staining	4-5	4-5	4-5	2-3
Conclusion		Pass	Pass	Pass	--

Colour Fastness to Rubbing					
(ISO 105-X12: 2016; Size of rubbing finger: 16mm diameter.)					
		No.5	No.6	No.12	Client's Limit
Length	Dry staining	4-5	4-5	4-5	2-3
	Wet staining	4-5	4-5	4-5	2-3
Width	Dry staining	4-5	4-5	4-5	2-3
	Wet staining	4-5	4-5	4-5	2-3
Conclusion		Pass	Pass	Pass	--

Note:

(1) Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

Description for Specimen:

Specimen No.	Specimen Description
1	Blue white main fabric
2	Black white main fabric
3	Red white main fabric
4	Black fabric rim
5	Black webbing
6	Black main fabric
7	Black zipper fabric
8	Black plastic zipper tooth
9	Silvery metal zipper head with black coating
10	Black plastic hook(VELCRO)
11	Black plastic loop(VELCRO)
12	Black lining



Report No.: WTF22F10216847C

Photograph of parts tested:





Report No.: WTF22F10216847C

Remarks:

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report =====

WALTEK